

Grades	UNS	France	Germany	Japan	Russia	European	Russian	British	Other Names
High-Nickel		AFNOR	WNR/DIN	JIS	GOST	EURONORM	OR	BS	
Inconel 600	N06600	NC15FE11M	2.4816	NCF 600	XH60BT	NiCr15Fe	ЭИ868	NA 14	Alloy 600/Nickel 600
Inconel 601	N06601	NC23FeA	2.4851	NCF 601	XH60BT	NiCr23Fe	ЭИ868	NA 49	Alloy 601/Nickel 601
Inconel 625	N06625	NC22DNB4M	2.4856	NCF 625	XH75MБTЮ	NiCr22Mo9Nb	ЭИ602	NA 21	Alloy 625/Nickel 625
Inconel 800HT	N08811	-	1.4959/1.4876	NCF 800HT	XH32T	X8NiCrAlTi32-21	ЭИ670	NA 15(HT)	Incoloy 800 HT/Alloy 800 HT
Inconel 800H	N08810	Z8NC33-21	1.4958/1.4876	NCF 800H	XH32T	X5NiCrAlTi31-20	ЭИ670	NA 15(H)	Incoloy 800H/Alloy 800 H
Inconel 800	N08800	Z8NC32-21	1.4876	NCF 800	XH32T	X10NiCrAlTi32-20	ЭИ670	NA 15	Incoloy 800/Alloy 800
Inconel 825	N08825	NC 21 FeDU	2.4858	NCF 825	XH38BT	NiCr21Mo	ЭП703	NA 16	Incoloy 825/Alloy 825
Hastelloy C276	N10276	-	2.4819	NW 0276	XH65MBY	NiMo16Cr15W	ЭП760	-	Alloy C276/Inconel C276
Hastelloy C22	N06022	NU-30M	2.4602	-	-	NiCr21Mo14W	-	-	Alloy C22/Hastelloy C
Monel 400	N04400	NU3	2.436/NiCu30Fe	-	-	-	-	NA 30	Alloy 400/Nickel 400
Alloy 20	N08020	Z2NCUD31	2.466	-	-	NiCr20CuMo	-	-	Carpenter 20/Nickel 20